

Shanghai PingYiao Trading CO., Ltd.

ArChine Refritech AHT 100

Ammonia Refrigeration Compressor Fluid

PRODUCT DESCRIPTION

ArChine Refritech AHT 100 is premium semisynthetic hydro-treated oil designed for ammonia applications. ArChine Refritech AHT 100 is specially formulated to resist degradation when exposed to acids formed when compressed ammonia comes into contact with the oil and condensed water. ArChine Refritech AHT 100 has excellent oxidation resistance and thermal stability at high temperatures to minimize sludge and varnish formation, and provide long service life. It also has outstanding water-separating properties to minimize the formation of emulsions, protects system components against rust and corrosion, and is resistant to excessive foam buildup that can interfere with proper lubrication.

APPLICATIONS

- ArChine Refritech AHT 100 can be used for Ammonia Refrigeration applications. Especially effective in combating corrosion and promoting long life in ammonia compressor.
- ArChine Refritech AHT 100 has proven its versatility in reciprocating and screw compressor.
- Cold storage facilities
- Ice making machines

TYPICAL PROPERTIES*

ArChine Refritech AHT 100	Standard Specification
Appearance	Colorless clear liquid
Density, 20°C, g/cm ³	0.858
Kinematic Viscosity@40°C, mm ² /s	99.8
Kinematic Viscosity@100°C, mm ² /s	11.98

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd.Tel: 86-21-64705533Adress: A1207, Yinhai Building, No.250, Caoxi Road, Xuhui District , Shanghai200235 P.R.ChinaTelephone helpline: (86)15900706965Website: www.pingyiao.comE-mail: info@pingyiao.com



Shanghai PingYiao Trading CO., Ltd.

Viscosity Index	110
Flash Point, Open Cup, °C	262
Pour Point, °C	-36
Copper Corrosion, 100°C, 3h	1

Shandhai Pineo Iradineo Co. *These values are not intended for use in preparing specifications.

Distributor WantedShanghai PingYiao Trading CO., Ltd.Tel: 86-21-64705533Adress: A1207, Yinhai Building, No.250, Caoxi Road, Xuhui District , Shanghai200235 P.R.ChinaTelephone helpline: (86)15900706965Fax: 86-21-64705533-209Website: www.pingyiao.comE-mail: info@pingyiao.com